

TEXTILENE® 90

BRAND FABRIC



TEXTILENE® 90

BRAND FABRIC

TEXTILENE® 90 son tejidos sintéticos duraderos hechos de poliéster recubierto de PVC. Diseñadas para reducir la transferencia de calor y el resplandor solar, nuestras telas reducen el deslumbre y los rayos perjudiciales del sol . Resistentes a la decoloración, son excelentes opciones para una variedad de usos en interiores o exteriores.

TEXTILENE® 90 bloquea hasta el 90% de los rayos solares.



TEXTILENE® 90

BRAND FABRIC

White
126" = 320.04 cm

Desert Sand
126" = 320.04 cm

Sandstone
126" = 320.04 cm

Dusk Grey
126" = 320.04 cm

Brown
126" = 320.04 cm

Black/Brown
126" = 320.04 cm

Textilene Exterior Window Shade Solar Screen

							Shading Coefficient						
Profile	Total Solar			Visible			UV	O.F.	1/8"	1/4"	1/4"	Clr. Dbl.	HA/Dbl.
Angle	Trans.	Ref.	Abs.	Trans.	Ref.	Abs.	Trans.		Clr.	Clr.	Clr.		
0	0.13	0.0	0.83	0.14	0.06	0.78	0.15	0.13	0.23	0.23	0.22	0.19	0.16
45	0.09	0.06	0.86	0.11	0.06	0.83	n/a	n/a	0.19	0.19	0.18	0.15	0.14

INFORMACIÓN TÉCNICA

Attribut	ASTM	Warp	Fill	Typical
Construction, end/inch	D3775-12	20.0 ±0.5	18.0 ±0.5	
Weight, 2 oz/yd Weigh2t, g/m Tensile	D3776-09			15.8
Strength (grab), lbf / daN Tensile	D3776-09			535.8
Strength (strip), lbf / daN Tear	D5034-09	608.3/275.9	527.3/239.2	
Strength (trapezoidal), lbf / daN	D5035-11	269.8/121.9	225.3/102.2	
Elongation, %	D5733	68.3/31.0	67.6/30.7	
Abrasion Resistance (CS10/500 cycles/ with no added weight)	D5035-11	29.3	29.8	
Flammability Rating	D3884-09		No Exposure of Core Yarn	
Weatherability, 1200 hours			CA Title 19 & NFPA 701	
Mildew Resistance	G154		Trace Discoloration	
Thickness, inches/mm	G21-13		No growth	
	D1777-96			.0345"/.8763mm

TEXTILENE 90

Excelente factor de sombra de hasta el 90%

CERTIFICACIONES



REACH
COMPLIANCE



GREENGUARD
GOLD



FLAME
RESISTANT



LEAD
FREE



ANTIMICROBIAL



PRINTABLE



RoHS
COMPLIANT



LIMITED
WARRANTY



TOY ACT



MADE IN USA