

# Geogrid/nonwoven composite



NAUE GmbH & Co. KG  
Gewerbestr. 2  
32339 Espelkamp-Fiestel  
Germany

Phone: +49 5743 41-0 Fax: +49 5743 41-240  
E-Mail: info@naue.com Internet: www.naue.com

## Combigrid® 30/30 Q1 151 GRK 3

### Product description:

Composite of a laid geogrid made of stretched, monolithic polypropylene (PP) flat bars with welded junctions and a mechanical bonded filter geotextile welded within the geogrid structure, used for the reinforcement in many fields of civil engineering including road construction, landfill and hydraulic engineering

Property	Test method*	Unit	30/30 Q1 151 GRK 3
<b>Geogrid</b>			<b>30/30 Q1</b>
Raw material	-	-	polypropylene (PP), white
Mass per unit area	EN ISO 9864	g/m <sup>2</sup>	200
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	≥ 30 / ≥ 30
Elongation at nominal strength, md / cmd**	EN ISO 10319	%	≤ 8 / ≤ 8
Tensile strength at 1% elongation, md / cmd**	EN ISO 10319	kN/m	6 / 6
Tensile strength at 2% elongation, md / cmd**	EN ISO 10319	kN/m	12 / 12
Tensile strength at 5% elongation, md / cmd**	EN ISO 10319	kN/m	24 / 24
Aperture size, md x cmd**	-	mm x mm	approx. 32 x 32
Production specific elongation	-	%	0
<b>Geotextile</b>			<b>151 GRK 3</b>
Raw material	-	-	polypropylene (PP), white
Mass per unit area	EN ISO 9864	g/m <sup>2</sup>	≥ 150
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	7.5 / 11.0
Elongation at max. tensile strength, md / cmd**	EN ISO 10319	%	40 / 30
Puncture force	EN ISO 12236	N	1,670
Displacement at static puncture strength	EN ISO 12236	mm	30
Detector tested	-	-	yes
Roll dimensions, width x length	-	m x m	4.75 x 100

\*based on, \*\*md = machine direction, cmd = cross machine direction

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.

revision date: 31 March 2014

Combigrid Q1.xlsx\_30'30 Q1 151 GRK 3\_e