

Geogrid

Secugrid® Q (PP)



NAUE GmbH & Co. KG
 Gewerbestr. 2
 32339 Espelkamp-Fiestel
 Germany
 Phone: +49 5743 41-0 Fax: +49 5743 41-240
 E-Mail: info@naue.com Internet: www.naue.com

Product description:

Laid geogrid made of stretched, monolithic polypropylene (PP) flat bars with welded junctions used for the reinforcement in many fields of civil engineering including landfill engineering, road construction and hydraulic engineering

Property	Test method*	Unit	20/20 Q1	30/30 Q1	40/40 Q1	60/60 Q1	80/80 Q1	
Raw material	-	-	polypropylene (PP), white					
Mass per unit area	EN ISO 9864	g/m ²	155	200	240	360	440	
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	≥ 20 / ≥ 20	≥ 30 / ≥ 30	≥ 40 / ≥ 40	≥ 60 / ≥ 60	≥ 80 / ≥ 80	
Elongation at nominal strength, md / cmd**	EN ISO 10319	%	≤ 8 / ≤ 8					
Tensile strength at 1% elongation, md / cmd**	EN ISO 10319	kN/m	4 / 4	6 / 6	8 / 8	12 / 12	16 / 16	
Tensile strength at 2% elongation, md / cmd**	EN ISO 10319	kN/m	8 / 8	12 / 12	16 / 16	22 / 22	25 / 25	
Tensile strength at 5% elongation, md / cmd**	EN ISO 10319	kN/m	16 / 16	24 / 24	32 / 32	48 / 48	50 / 50	
Aperture size, md x cmd**	-	mm x mm	approx. 33 x 33	approx. 32 x 32	approx. 31 x 31	approx. 31 x 31	approx. 31 x 30	
UV-resistance (remaining tensile strength)	EN 12224	%	95.0					
Weather resistance	FGSV	class	high					
Production specific elongation	-	%	0					
Roll dimensions, width x length	-	m x m	4.75 x 100					

*based on, **md = machine direction, cmd = cross machine direction

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.

revision date: 15 May 2014

Secugrid Q1.xlsx 20', 30', 40', 60', 80' Q1_e



¡Contáctanos!

info@ldm.la www.ldm.la

USA +1 480 894 5232

MÉXICO +52 662 108 0020

COLOMBIA +57 601 829 5511

PANAMÁ +507 2 308 7585