

# World of Coats *dabond*

COATS  
*dabond*



BONDED  
CONTINUOUS  
FILAMENT  
POLYESTER

Product Information



Coats *dabond* is a bonded, twisted continuous filament polyester thread. Combining superior sewing performance with excellent UV and abrasion protection, Coats *dabond* is specifically designed to provide resistance against harsh weather conditions. Coats *dabond* can withstand UV degradation in all outdoor applications that are exposed to marine water and sunlight.

#### Main Uses:

- Sail making
- Boat tops
- Flags
- Military supplies
- Tents and awnings
- Canvas and tarps
- Inflatables / hot air balloons
- Marine lift slings and tie downs
- Applications requiring vinyl and chlorine bleach-fastness



#### Features and Benefits:

- Coats *dabond* has excellent UV resistance for applications exposed to marine water and sunlight
- Unique bonding technology that safeguards against ply untwisting in zig zag sewing and can sew through many layers of heavily finished fabric
- Dual level lubricated finish for needle heat protection and smooth sewing
- Excellent bleach, mildew and rot resistance
- Coats *dabond* is the only environmentally-friendly bonded polyester thread available in the market
- The industry standard for sail making and other outdoor and marine applications
- Special version of in-line dyed Coat *dabond* available for excellent vinyl fastness

## World of Coats

- Coats is the largest global thread supplier and has been the world's leading thread company for over 200 years.
- With manufacturing plants in over 70 locations and sales and distribution in more than 80 countries, Coats is uniquely placed to serve your thread needs anywhere in the world.
- Our state of the art colour communications management system, Coats ColourStitch®, enables exact sample matching and colour approval almost instantaneously between locations around the globe.

#### One colour range. One specification. Worldwide.

Coats operates to a global specification for Coats *dabond* with quality audited by a centrally located team.

[www.coatsindustrial.com](http://www.coatsindustrial.com)



**BONDED  
CONTINUOUS  
FILAMENT  
POLYESTER**

Product Information



**Product Guidelines:**

Tex No.	Ticket No. (Nm)	Ply	Average Strength		Elongation % Min - Max	Recommended Needle Size*	
			cN	Grams		Singer	Metric
30	100	2	2,058	2,099	12 - 22	12 - 16	80 - 100
35	80	3	2,130	2,172	12 - 24	12 - 16	80 - 100
45	60	2	2,400	2,447	12 - 24	14 - 18	90 - 110
60	50	2	3,330	3,396	12 - 24	14 - 18	90 - 110
70	40	3	4,250	4,334	12 - 24	16 - 19	100 - 120
80	35	3	5,195	5,297	12 - 24	19 - 22	120 - 140
90	30	4	6,468	6,600	12 - 24	19 - 22	120 - 140
105	25	4	6,664	6,800	12 - 24	19 - 22	120 - 140
135	20	3	8,085	8,244	12 - 24	21 - 23	130 - 160
150	18	3	8,820	8,994	16 - 28	21 - 23	130 - 160
210	13	3	12,000	12,236	16 - 28	22 - 24	140 - 180
240	12	3	14,430	14,714	16 - 28	23 - 25	160 - 200
270	10	3	17,000	17,335	14 - 26	23 - 25	160 - 200
350	9	3	20,000	20,394	14 - 26	23 - 25	160 - 200
400	8	3	27,930	28,480	15 - 30	24 - 26	180 - 230
450	7	3	29,400	29,979	14 - 26	24 - 26	180 - 230
500	6	6	37,730	38,473	15 - 30	25 - 27	200 - 250
700	4	6	46,158	47,067	15 - 30	27 - 29	250 - 300

\* Needle size recommendations are a guide only and ultimately depend on the sewing application. Since conditions and applications vary considerably in the use of thread, the thread user should assure herself or himself by preliminarily testing that the thread is suitable for the end use intended. Technical information listed above is based on current averages and should be taken only as indicative.

- UV-inhibitor filaments used in all sizes 220 denier and above
- Special finishes available: anti-wick, high lube, FR
- Make Up (King Spool): - By length (Meters): 1000, 1500, 2500  
- By weight (Kgs): 0.113, 0.227, 0.454, 0.907

Coats *dabond* [belbobs and barbobs]


Tex	Ticket	Style	Meters / Belbobs	Tex	Ticket	Style	Meters / Belbobs
30	80	G	78	135	20	U	30
-	-	U	151	-	-	39	29
70	40	U	51	210	13	58	43
90	30	FD	24	270	10	A	6*
-	-	G	21	350	9	X	60
-	-	J	34	400	8	X	48
-	-	MD	36	-	-	41	48
135	20	M	22	-	-	-	-

\* Barbob (with side and with core)

Only popular bobbin styles listed. All yardages are approximate and are for bonded colours.

**Bobbin Benefits:**

- 5-20% machine productivity increase, precision wind for uniform pull-off tension, improved stitch appearance.



**Physical and chemical properties of bonded continuous filament polyester:**

**Thermal Properties:**

- Melting point 250 - 260°C
- Special in-line dyed Coats *dabond* available for UV fade resistance of 4 - 5

**Chemical Properties:**

- Mineral acids: Resistant to most mineral acids
- Alkalis: Essentially unaffected by weak alkalis, but less resistant to stronger alkalis, especially at higher temperatures
- Organic solvents: Generally unaffected, but soluble in some phenolic compounds
- Bleaching: Excellent resistance
- Insects / microorganisms: Unaffected
- Moisture regain: Approximately 0.4% (drip dry)

**Coats *dabond* fastness properties:**

- Wash Fastness (ISO 105 C06) Grade 4 - 5
- Water Fastness (ISO 105 E01:2010) Grade 4
- Rub Fastness (ISO 105 X12:2001) Grade 3 - 4  
(4 - 5 for in-line dyed version)
- Vinyl Transfer (CTC-TP-1032-003) Grade 5  
(for in-line dyed version)

Since conditions and applications vary considerably in the use of thread, the thread user should assure himself by preliminary testing that the thread is suitable for the end use intended.

